



Contribution ID: 664

Type: Oral Presentation

FTP/4-5Ra & FTP/4-5Rb: Optimisation of a Nanostructured ODS Ferritic Steel Fabrication towards Improvement of its Plasticity; Low Activation Vanadium Alloys for Fusion Power Reactors - the RF Results

Friday, 12 October 2012 18:00 (20 minutes)

FTP/4-5Ra: Optimisation of a Nanostructured ODS Ferritic Steel Fabrication towards Improvement of its Plasticity

In order to increase the operation temperature of the high-chromium reduced activation steels foreseen in applications of fusion reactors, ferritic steels containing 12 to 14% Cr in weight and reinforced with a dispersion of nano-oxides are being under development. The nano-oxides are incorporated into the matrix by adding Y₂O₃ or Fe-Y intermetallic particles to the initial steel powder, and by performing an intensive ball milling. In order to produce an ODS-steel with better mechanical properties, two specific actions of the production route were considered in this work to minimize the air contamination and porosity. The first one consists in using a higher purity pre-alloyed steel powder instead of mixture of elemental powders. The second one is to perform an additional densification after the hot-isostatic pressing (HIP) by hot cross rolling (HCR) the consolidated HIPed ingot.

The steel powders batches were produced by ball milling of either elemental or pre-alloyed powders with Y₂O₃ or Fe₂Y reinforcement particles in attritor, applying a hydrogen milling atmosphere at a controlled pressure and subsequent hot isostatic pressing. The influence of the type of substrate powders on the mechanical properties was studied for the ODS steels after HIP and after a thermal-mechanical treatment. HCR were applied at a temperature of 800°C.

Optical microscope observations revealed a refinement of the microstructure with smaller porosity. Transmission electron microscope observations of the HCR ODS steel samples microstructures showed mainly recovered grains but also a slight coarsening of the finest oxides particles compared with the steel after HIP. Grains elongation in the rolling plane or in the normal plane was not observed. Hot cross-rolling resulted in an increase of ultimate tensile strength and a significant decrease of the ductile to brittle transition temperature (DBTT). While a lower DBTT has been found for the ODS steels on which HCR was applied, it remains that the upper shelf energy is relatively low in comparison to conventional steel, about twice as low. Thus, more activities are required to produce a material possessing a better balance between the desired high tensile strength, low DBTT and high value of the upper fracture shelf energy. Possible modifications in the fabrication to reach that goal will be discussed.

FTP/4-5Rb: Low Activation Vanadium Alloys for Fusion Power Reactors - the RF Results

The Results of development and researches of functional properties of low activation vanadium alloys (V-Ti-Cr and V-Cr-W-Zr-C systems) being developed for the cores of nuclear fusion and fission (Gen-IV, space) power reactors are presented.

Scientific and technological problems of the investigations are related with enhancement of functional properties based on (1) special optimized thermal (TT), thermomechanical (TMT) and thermochemical (TCT) treatments of V-4Ti-4Cr alloys, and (2) development of new (V-Cr-W-Zr-C system) vanadium alloys.

The TMT and TCT regimes ensuring the capability of significant (up to 2 times) enhancement of yield strength in the temperature range up to 800 C keeping relatively high plasticity reserve have been found for alloys.

The results of the theoretical, modeling and simulating studies of characteristics of self-point defects and dislocations, their interactions and mobility are presented. Nuclear physics characteristics (primary radiation

damage, activation, transmutation, postreactor cooling) of alloys irradiated for a long time in neutron spectra of the fusion reactor DEMO-RF (15,3 dpa/year) and fast power reactor BN-600 (80 dpa/year) are calculated. The interaction characteristics of V-4Ti-4Cr alloy with hydrogen and the influence of hydrogen on mechanical properties of the alloy (impact toughness, internal friction) have been studied. Obtained results allows one to recommend the vanadium alloys for applications in nuclear reactors at operating temperature window 300 C –800(850) C. The planes of high-dose and high-temperature reactor tests of vanadium alloys are scheduled at material science assemblies of reactor BN-600 (2013 –2015, doses 50 –200 dpa, irradiation temperatures 400 C–800 C).

Country or International Organization of Primary Author

Switzerland

Primary authors: Dr UNIFANTOWICZ, Paulina (CRPP, EPFL, Switzerland); Prof. CHERNOV, Viacheslav (A.A.Bocvar High-technology Research Institute of Inorganic Materials)

Presenter: Mr FIKAR, Jan (Switzerland)

Session Classification: Fusion Materials and Neutron Sources

Track Classification: FTP - Fusion Technology and Power Plant Design