

# Erosion and deposition in the JET divertor during the ITER-like wall campaigns

*Tuesday 23 October 2018 08:30 (20 minutes)*

During JET operation with all carbon walls prior to 2010 (JET-C) massive re-deposition of previously eroded carbon was observed in the divertor and in remote divertor areas. This massive carbon re-deposition was accompanied by a high retention of hydrogen isotopes trapped by co-deposition. Extrapolations of these results to ITER predicted very high potential tritium retention, resulting in the decision to remove carbon from the ITER divertor.

One aim of the JET ITER-like wall (JET-ILW) project was to study plasma-surface interactions in a carbon-free beryllium/tungsten environment comparable to the ITER material configuration. All divertor tiles were manufactured either from tungsten coated carbon-fibre composite (CFC) material or from bulk tungsten. Erosion and deposition in the JET divertor were studied during the campaigns JET-ILW1 (2011-2012), ILW-2 (2013-2014) and ILW-3 (2015-2016) by using specially prepared divertor marker tiles using W/Mo marker layers, which were analysed before and after the campaign using elastic backscattering of 3 and 4.5 MeV incident protons and nuclear reaction analysis using 0.8 to 4.5 MeV  $^3\text{He}$  ions.

The erosion/deposition pattern observed with the JET-ILW configuration shows partly drastic changes compared to the pattern observed with JET-C: The total material deposition rate in the divertor decreased by a factor of 4–9 compared to the deposition rate of carbon in JET-C. This decrease of material deposition in the divertor is accompanied by a decrease of total deuterium retention inside the JET vessel by a factor of about 20.

The erosion/deposition pattern observed during JET ILW-2 was qualitatively comparable to JET ILW-1, the observed D inventory was roughly comparable to the inventory observed during JET ILW-1. The results obtained during JET ILW-2 therefore confirm the positive results observed in JET ILW-1. Early results from JET ILW-3 also indicate agreement; more details will become available in summer 2018.

## Country or International Organization

Germany

## Paper Number

EX/P1-15

**Author:** Dr MAYER, Matej (Max-Planck-Institut für Plasmaphysik)

**Co-authors:** Dr BARON-WIECHEC, Alexandra (Culham Centre for Fusion Energy, Culham Science Centre); Dr WIDDOWSON, Anna (UKAEA); Dr RUSSET, Cristian (National Institute for Laser, Plasma and Radiation Physics); Dr JEPU, Ionel (National Institute for Laser, Plasma and Radiation Physics); Dr LIKONEN, Jari (VTT Technical Research Centre of Finland); Dr HEINOLA, Kalle (University of Helsinki); Dr COAD, Paul (Culham Centre for Fusion Energy, Culham Science Centre); Dr PETERSSON, Per (Fusion Plasma Physics, Royal Institute of Technology); Dr BREZINSEK, Sebastijan (Forschungszentrum Jülich); Dr KRAT, Stepan (National Research Nuclear University MEPhI); Dr GASPARYAN, Yury (National Research Nuclear University MEPhI)

**Presenter:** Dr MAYER, Matej (Max-Planck-Institut für Plasmaphysik)

**Session Classification:** P1 Posters