Contribution ID: **610** Type: **Poster**

Effect of defect concentration and distribution on hydrogen isotope retention and diffusion in damaged W for fusion first wall

Thursday, 20 October 2016 08:30 (4 hours)

Elucidation of tritium dynamics is one of the key issues for sustainable D-T fusion. Tungsten will be exposed to high fluxes of tritium (T) accompanied with various energetic particles. Therefore, T retention and its trapping states will be dramatically changed by the accumulation of ion and neutron-induced damage and recovery by heating. These facts motivate us to perform extensive hydrogen isotope retention experiments in damaged W under the framework of Japan/US joint project, PHENIX. This paper presents recent results, including an analysis of D retention by various methods over a range of defect concentrations.
Disks of stress-relieved W were irradiated using 6 MeV Fe2+ at room temperature in TIARA, JAEA or 6.4 MeV Fe3+ at higher temperature in DuET, Kyoto University up to 1.0 dpa. These samples were then compared with neutron-damaged W (10-6 dpa for 14 MeV or 10-4 dpa for thermal neutrons). All the samples were exposed to 1 keV D2+ up to a fluence of 1.0 × 1022 D m-2 at room temperature. Thereafter, thermal desorption spectroscopy (TDS) was applied with the heating rate of 0.5 K s-1 up to 1173 K.
The D2 TDS spectra from Fe2+ damaged W showed that accumulation of damage shifted to higher desorption temperature, consistent with the formation of large voids. For W specimens damaged by 14 MeV fusion neutrons to 10-6 dpa, the D2 desorption at 700 K was found even at low defect concentrations, suggesting that the collision cascades result in the formation of vacancies. The simulations showed that D accumulated within 0.5 ⊠m of the exposed surface for W damaged by Fe2+ ions.
The results of D permeation experiment showed that D permeability for damaged W was reduced by damage introduction. Furthermore, by heating above 1100 K, D permeability were completely consistent with that for undamaged W. The nature of the defects is critical, and their stability will strongly influence D permeability.
In summary, the accumulation of defects resulted in the formation of stable trapping sites. The D trapping by defects reduces the number of available D diffusion pathways through the lattice, a mechanism that could lead to a reduction of D permeability. Finally, we note that dynamic recovery of damages is enhanced by high temperature irradiation.

Paper Number

MPT/P5-31

Country or International Organization

Japan

Primary author: Dr OYA, Yasuhisa (Shizuoka University)

Co-authors: Dr TAYLOR, Chase (Idaho National Laboratory); Dr DONOVAN, David (University of Tennessee at Knoxville); Dr BUCHENAUER, Dean (Sandia National Laboratories); Dr KATAYAMA, Kazunari (Kyushu Uni-

versity); Mr OYA, Makoto (Graduate school of Engineering, Osaka University); Dr SHIMADA, Masashi (Idaho National Laboratory); Prof. YOSHIDA, Naoaki (Kyushu University); Dr TEPPEI, Otsuka (Kyushu University); Dr KOLASINSKI, Robert (Sandia National Laboratories); Dr KONDO, Sosuke (Kyoto University); Dr TOYAMA, Takeshi (Tohoku University); Dr CHIKADA, Takumi (Shizuoka University); Dr HINOKI, Tatsuya (Kyoto University); Prof. UEDA, Yoshio (Osaka University); Prof. HATANO, Yuji (Hydrogen Isotope Research Center, University of Toyama); Dr NOBUTA, Yuji (Hokkaido Univ.); Dr YAMAUCHI, Yuji (Hokkaido University); Dr HAMAJI, Yukinori (National Institute for Fusion Science)

Presenter: Dr OYA, Yasuhisa (Shizuoka University)

Session Classification: Poster 5

Track Classification: MPT - Materials Physics and Technology